

Attorney Docket No.: KUZ-0022
Inventors: Ito et al.
Serial No.: 10/527,710
Filing Date: April 22, 2005
Page 2

This listing of the claims will replace all prior versions and listings of claims in the application:

Listing of the claims:

Claim 1 (currently amended): An adhesive patch for maintaining a long-term drug efficacy comprising a backing layer and a pressure-sensitive adhesive layer formed on one side thereof, wherein the pressure-sensitive adhesive layer consists essentially of fentanyl as an active ingredient, a pressure-sensitive adhesive base, and a tackifier resin, wherein the pressure-sensitive adhesive base comprising comprises polyisobutylene and a styrene/isoprene/styrene block copolymer, the proportion of the polyisobutylene in the adhesive base being 8 to 15 wt.%, and a ratio of a concentration of the polyisobutylene to that of the styrene/isoprene/styrene block copolymer being from 2:3 to 3:2, and wherein the tackifier resin is an alicyclic saturated petroleum resin and a proportion of the tackifier resin is from 40 to 50 wt.%.

Claim 2 (original): The adhesive patch according to claim 1, wherein the concentration of fentanyl is 1 to 6 wt.%.

Claim 3 (previously presented): The adhesive patch according to claim 1, wherein the polyisobutylene consists of a high molecular weight polyisobutylene and a low molecular weight polyisobutylene.

Attorney Docket No.: **KUZ-0022**
Inventors: **Ito et al.**
Serial No.: **10/527,710**
Filing Date: **April 22, 2005**
Page 3

Claim 4 (original): The adhesive patch according to claim 3, wherein an average molecular weight of the high molecular weight polyisobutylene is 900,000 to 2,500,000.

Claim 5 (previously presented): The adhesive patch according to claim 3, wherein an average molecular weight of the low molecular weight polyisobutylene is 30,000 to 65,000.

Claim 6 (currently amended): The adhesive patch according to claim 1, wherein the tackifier resin is ~~an alicyclic saturated hydrocarbon~~ hydrogenated petroleum resin.

Claim 7 (currently amended): The adhesive patch according to claim 1, wherein a proportion of the tackifier resin is ~~40~~ 44.5 to 50 wt.%.

Claim 8 (currently amended): An adhesive patch for maintaining a long-term drug efficacy comprising a backing layer and a pressure-sensitive adhesive layer formed on one side thereof, wherein the pressure-sensitive adhesive layer ~~consisting~~ consists of fentanyl as an active ingredient, a pressure-sensitive adhesive base, a percutaneous absorption enhancer, and a tackifier resin, wherein the pressure-sensitive adhesive base ~~comprising~~ comprises polyisobutylene and a styrene/isoprene/styrene block copolymer, the proportion of the polyisobutylene in the adhesive base being 8 to 15 wt.%, and a ratio of a concentration of the polyisobutylene to that of the styrene/isoprene/styrene

Attorney Docket No.: KUZ-0022
Inventors: Ito et al.
Serial No.: 10/527,710
Filing Date: April 22, 2005
Page 4

block copolymer being from 2:3 to 3:2, and wherein the
tackifier resin is an alicyclic saturated petroleum resin
and a proportion of the tackifier resin is from 40 to 50
wt.%.

Claim 9 (original): The adhesive patch according to
claim 8, wherein the percutaneous absorption enhancer is one
or more selected from a group consisting of isopropyl
myristate, isopropyl palmitate, sorbitan monooleate and
oleyl alcohol.

Claim 10 (previously presented): The adhesive patch
according to claim 1, having an area of 10 to 75 cm² at the
time of application.